

THERMOZELL

pro speed

PRODUCT DATA SHEET

The optimal starting material for the professional and the construction site. Tested and approved by building authorities since 1995.

Pretreated recycled EPS* granulate with general building authority approval/design approval (Z-23.11-266) for your project.

www.thermozell.com



Anwendung 3in1



Level compensation

Installations, beam ceiling, vault, slope, etc



Foundation

Screeds, tiling, underfloor heating, etc



Backfill

Wall, ceiling, pool, etc

Ready for covering

Ready for covering

in 24 hours

Simplest Processing 100% EPS recyclate

- approx. 24 days (depending on <12 % CM measurement/construction climate)

Construction height

- at least 3 cm

Yield

- 1 bag yields approx. 200 liters of readymixed lightweight concrete

Processing time and temperature

- at least 15 minutes at 20° C
- not under 5° C

Suitable mixing equipment

- Screed pump
- Mixing truck



Refined High Performance Granule



Processing









The mixing process with the addition of cement and water takes place at the construction site. Different amounts of cement are added to produce the product types pro 600, 400, 250 and 160 speed with the respective properties.

Technical data:

- 1 Design value of thermal conductivity W/mK 2 Bulk density of dry mixture kg/m³
- 3 Bulk density of the fresh concrete mortar 4 Dry bulk density of the bound EPS kg/m³
- 5 Compressive strength kPA 6 Water vapor diffusion resistance μ 7 Fire behavior
- 8 Binder content per m³

	Thermozell pro 600 speed	Thermozell pro 400 speed	Thermozell pro 250 speed	Thermozell pro 160 speed
1	≤ 0.180	≤ 0.120	≤ 0.090	≤ 0.066
2	400 +/- 5 %	275 +/- 5 %	210 +/- 5 %	150 +/- 5 %
3	615 – 700	395 – 445	325 – 375	150 – 200
4	500 +/- 10 %	350 +/- 10 %	250 +/- 10 %	165 +/- 15 %
5	≥ 1.200	≥ 500	≥ 200	≥ 70
6	14	7	7	5
7	A2	A2	E	E
8	375 kg	250 kg	187.5 kg	125 kg

Storage

- The bag must be stored in a dry place
- Maximum storage time: 1 year

Packaging units

- 1 bag = 200 liters
- -1 pallet = 12 bags (2.4 m³)

Other instructions

- No compaction necessary
- During planning and installation, the standards and guidelines of the respective country must be observed

www.thermozell.com

Refined High Performance Granule

